

REMARKS

Applicant believes that the application is now in condition for immediate allowance. In the event the Examiner finds any remaining impediment to a prompt allowance of the claims which could be clarified or satisfied by a telephonic discussion or interview, the Examiner is respectfully requested to initiate the same with the undersigned attorney.

DATED this 30TH day of April 2002.

Respectfully submitted,

Kevin B Laurence

Kevin B. Laurence
Attorney for Applicant
Registration No. 38,219



03528

PATENT TRADEMARK OFFICE

20060515 043000

VERSION WITH MARKINGS TO SHOW CHANGES MADE IN THE CLAIMS:

Please amend claims 1-4, 6-8, 14-15, 17-18, 20, 23, and 25 as follows:

Please delete claims 5, 9-13, 16-24 and 26-32.

1. (Amended) A method for preparing mesophase pitch-based tape comprising
the step of:

extruding mesophase pitch through a slot-shaped die with an aspect ratio of
[10] 50 or more and drawing at a draw ratio greater than 5[.], wherein the shear rate in
the die is in the range 1000 to 5000s⁻¹.

2. (Amended) A method as claimed in claim 1 further comprising[:]
the step
of stabilising the mesophase pitch-based tape.

3. (Amended) A method as claimed in claim 1 [or 2] further comprising[:] the
step of oxidatively stabilising the mesophase pitch-based tape.

4. (Amended) A method as claimed in [any preceding] claim 1 wherein [the
planar molecules arrange mainly parallel to the major surface of] the mesophase pitch-based
tape has a major surface and planar molecules arranged mainly parallel to the major surface.

6. (Amended) A method as claimed in [any preceding] claim 1 wherein the
mesophase pitch based tape is subjected to an elevated temperature.

7. (Amended) A method as claimed in [any preceding] claim 1 wherein the
aspect ratio of the die is [20 or more, particularly preferably 30 or more, more preferably 40

or more, more especially preferably about 50 or more, even more especially preferably] 60 or more[, yet even more especially preferably 70 or more].

8. (Amended) A method as claimed in [any preceding] claim 1 further comprising the step of carbonisation or graphitisation.

14. (Amended) A method as claimed in claim [9] 1 wherein [the die has an aspect ratio of about 50 and] the shear rate is in the range 1900 to 4000s⁻¹

15. (Amended) A method as claimed in claim [9] 1 wherein the [die has an aspect ratio of the die is about 80 and the shear rate is in the range 1700 to 4900s⁻¹.

17. (Amended) A method as claimed in [any preceding] claim 1 wherein the draw ratio is greater than 10.

18. (Amended) A method as claimed in [any preceding] claim 1 wherein the tape is of flat-layer transverse texture, said method further comprising[:]
the step of laminating the tape with a material capable of controlling the thermomechanical properties, transport properties or resistance to oxidation of the tape.

20. (Amended) A mesophase pitch-based tape obtainable from a method as defined in [any one of claims] claim 1 [to 19] comprising graphite basal planes parallel to the major surface of the tape.

23. (Amended) A mesophase pitch-based tape as claimed in [any of claims]
claim 20 [to 22] comprising a flat layer transverse texture.

25. (Amended) A mesophase pitch-based tape as claimed in [any of claims]
claim 20 [to 24] comprising an extended graphitic plane structure.

2003-10-25 16:00:01